A Parametric Study on J-integral under Pressurized Thermal Shock by Using Statically Indeterminate Fracture Mechanics

Masaaki MATSUBARA

Central Research Institute of Electric Power Industry, Tokyo, Japan

ABSTRACT

The author proposed one application of elastic-plastic fracture mechanics for a statically indeterminate structure to a two-dimensional crack problem in the pressure vessel of pressurized water reactor (PWR) under pressurized thermal shock (PTS). This method makes us to evaluate the J-integral in an explicit form and is efficient in clarifying the mechanical characteristics of the PTS event. This paper describes a parametric study of the J-integral under PTS using this technique.

1 INTRODUCTION

The J-integral is valid for elastic-plastic fracture mechanics analysis, especially in ductile fracture analysis. But the original J-integral proposed (Rice 1968) is not used for fracture mechanics analysis under thermal loading, because the J-integral does not keep its path independence in this case. Special path independent integrals have been proposed for this purpose, for example, the J-integral proposed (Aoki et al. 1981). These special integrals can only be evaluated by using a numerical analysis method, finite element method, etc. So the integrals are not generally familiar to engineers because of their difficulty and complexity. The author has proposed statically indeterminate elastic-plastic fracture mechanics (SIEPFM) and confirmed its validity for an application to a PTS problem in the CSNI Project FALSIRE. It can overcome the defect of the special path independent integrals, simplify evaluating the J-integral under PTS and clarify the fracture mechanics characteristics of the PTS event. This paper describes parametric study of the J-integral under PTS based on the application of SIEPFM to a PTS problem.

2 EVALUATION OF THE J-INTEGRAL

The hoop stress conferred by PTS is divided into three components, membrane stress, bending stress and stress with non-linear distribution balanced in the direction of wall thickness. SMiRT 11 Transactions Vol. G (August 1991) Tokyo, Japan, © 1991

SIEPFM is applied to evaluation of the J-integral due to membrane and bending stresses, those with linear distribution. It is assumed that circumferential force P and bending moment M are acting on the end surface of a cylindrical shell, which has a slit and combines with a cracked member with zero length (see Fig.2). The displacement u and rotation θ of the slit cylindrical shell must be respectively equal to the displacement Δu and rotation $\Delta\theta$ due to the crack. The following equation can be obtained;

$$u = \Delta u, \quad \theta = \Delta\theta \quad (1)$$

Once we evaluate the deformation of the shell and the cracked member as functions of P and M , we can conversely obtain P and M through equation (1). These are used to obtain the J-integral value. P and M are determined by the following procedure. The simultaneous equations of P and M are given by:

$$\left. \begin{aligned} f(P, M) &= (C_P + \Delta C_P)P + (C_{PM} + \Delta C_{PM})M \\ &+ \frac{\partial \Omega_{cp}}{\partial P} - C_P P_0 - C_{PM} M_0 + \Delta u_n = 0 \\ g(P, M) &= (C_{PM} + \Delta C_{PM})P + (C_M + \Delta C_M)M \\ &+ \frac{\partial \Omega_{cp}}{\partial M} - C_{PM} P_0 - C_M M_0 + \Delta \theta_n = 0 \end{aligned} \right\} \quad (2)$$

where Ω_{cp} is the complimentary energy (Parks et al. 1982). The equations are solved by the Newton-Raphson method:

$$\begin{bmatrix} f_P(P_i, M_i) & f_M(P_i, M_i) \\ g_P(P_i, M_i) & g_M(P_i, M_i) \end{bmatrix} \begin{Bmatrix} \delta P \\ \delta M \end{Bmatrix} = \begin{Bmatrix} -f(P_i, M_i) \\ -g(P_i, M_i) \end{Bmatrix} \quad (3)$$

$$\begin{aligned} \begin{Bmatrix} \delta P \\ \delta M \end{Bmatrix} &= \begin{bmatrix} f_P(P_i, M_i) & f_M(P_i, M_i) \\ g_P(P_i, M_i) & g_M(P_i, M_i) \end{bmatrix}^{-1} \begin{Bmatrix} -f(P_i, M_i) \\ -g(P_i, M_i) \end{Bmatrix} \\ &= \frac{1}{f_P \cdot g_M - f_M \cdot g_P} \begin{bmatrix} g_M & -f_M \\ -g_P & f_P \end{bmatrix} \begin{Bmatrix} -f(P_i, M_i) \\ -g(P_i, M_i) \end{Bmatrix} \end{aligned} \quad (4)$$

where $f_P = \frac{\partial f}{\partial P}$, $f_M = \frac{\partial f}{\partial M}$, $g_P = \frac{\partial g}{\partial P}$ and $g_M = \frac{\partial g}{\partial M}$.

Appropriate values, P_i and M_i are substituted into equation (4). If δP and δM are extremely small compared with P_i and M_i , calculation may be stopped. If no, recalculation must be made using new P_i ($=P_i + \delta P$) and M_i ($=M_i + \delta M$) until the above condition can be satisfied.

The J-integral can be obtained from the following equation by using the P and M values:

$$\begin{aligned} J &= J_{elastic} + J_{plastic} \\ &= \frac{1-\nu^2}{E} K^2 + \frac{1}{2} \alpha \epsilon_0 \sigma_0 W^2 \left(\frac{AP^2 + 2BPM/W + CM^2/W^2}{P_{ref}^2} \right)^{\frac{n-1}{2}} \\ &\quad \left\{ \frac{1}{P_{ref}^2} \left(\frac{\partial A}{\partial a} P^2 + 2 \frac{\partial B}{\partial a} \frac{PM}{W} + \frac{\partial C}{\partial a} \frac{M^2}{W^2} \right) - \frac{2}{P_{ref}^2} \frac{dP_{ref}}{da} \left(AP^2 + \frac{2BPM}{W} + \frac{CM^2}{W^2} \right) \right\} \end{aligned} \quad (5)$$

where σ_0 and ϵ_0 are the reference stress and strain, n is the hardening exponent, α is the coefficient in the Ramberg-Osgood law. A , B and C are derived from the fully plastic solution (Shih and Needleman 1984). The reference load P_{ref} is defined as:

$$\left. \begin{aligned} P_{ref} &= 1.455\sigma_0(W-a)\eta \\ \eta &= \left\{ 1 + \left(\frac{a}{W-a} \right)^2 \right\}^{\frac{1}{2}} - \frac{a}{W-a} \end{aligned} \right\} \quad (6)$$

3 RESULTS AND DISCUSSIONS

Fig.3 shows an effect of the constitutive law, the material constants in the Ramberg-Osgood law, on the J-integral under PTS. As evident from the figure, the J-integral under PTS is not significantly influenced by the constitutive law.

Fig.4 shows an effect of the thermal conductivity on the J-integral under PTS. The J-integral under PTS develops a tendency to small increase with a decrease of the thermal conductivity.

Fig.5 shows an effect of the heat transfer coefficient on the J-integral under PTS. The J-integral under PTS develops a tendency to increase with an increase of the heat transfer coefficient.

4 CONCLUSIONS

A parametric study was made on the J-integral under PTS by using SIEPFM. The following points were made clear;

(1)The J-integral under PTS is not significantly influenced by the constitutive law.

(2)The J-integral under PTS increases with a decrease of the thermal conductivity.

(3)The J-integral under PTS increases with an increase of the heat transfer coefficient.

ACKNOWLEDGMENTS

The author is grateful to Dr. D.M. Parks for his permission to refer to his unpublished manuscript.

REFERENCES

- Rice, J.R. (1968). A Path Independent Integral and the Approximate Analysis of Strain Concentration by Notches and Cracks, Journal of Applied Mechanics, Vol.35, pp.379-386.
- Aoki S. et al. (1981). (in Japanese), Transactions of the JSME, Series A, Vol.47, pp.304-312.
- Parks, D.M., Rodin, G.J. and Locket, R.R. (1982). The Line-Spring Model for J-Analysis of Surfaced-Cracked Plates and Shells: Calibration of the Power Law Spring, unpublished manuscript.
- Shih, C.F. and Needleman, A. (1984). Fully Plastic Crack Problems Part1: Solutions by a Penalty Method, Journal of Applied Mechanics, Vol.51, pp.48-56.

Table 1. Conditions considered in analysis.

Mean radius	(m)	2.0
Wall thickness	(m)	0.2
Initial temperature	(K)	580
Final temperature	(K)	300
Internal pressure	(MPa)	15
Young's modulus	(GPa)	193 — 206
Poisson's ratio		0.3
Constants of Ramberg-Osgood's law		
Coefficient		0.0208-1.12
Power's number		9.71 — 11.5
Reference stress	(MPa)	375 — 413.7
Reference strain		0.002
Coefficient of thermal expansion	(1/K)	1.5×10^{-5}
Specific heat	(kJ/(kgf·K))	0.5
Specific weight	(kgf/m ³)	7800
Thermal conductivity	(W/(m·K))	30 — 50
Coefficient of heat transfer	(W/(m ² ·K))	2500 — 7500
Cooling rate	(1/min)	∞

Fig. 1. Analysis model.

Fig. 2. Statically indeterminate fracture mechanics model.

Fig. 3. Effect of the constitutive law of the pressure vessel's steel on the J-integral under PTS.

Fig. 4. Effect of the thermal conductivity of the pressure vessel's steel on the J-integral under PTS.

Fig. 5. Effect of the heat transfer coefficient on the J-integral under PTS.