Elastic Creep-Fatigue Damage Evaluation: Less Restrictive Design Rules for SNR-2 Components

A. Angerbauer

INTERATOM GmbH, Postfach, D-5060 Bergisch-Gladbach 1, Germany

Abstract

To achieve less conservative design rules for LMFBR Class 1 components in elevated temperature service, two modifications of the elastic creep-fatigue evaluation in use are proposed: (1) In the creep-damage evaluation, the relaxation of residual stresses during hold-times shall be taken into account; (2) In the fatigue-damage evaluation, the creep effects on the cyclic stress-strain hysteresis loop shall be considered by adding the net relaxation strain during hold-times to the elastic-plastic strain range, and design fatigue curves without hold-time shall apply.

1. Introduction

For economical and practical reasons, the use of elastic methods is not to abandon in the design of LMFBR Class 1 components in elevated temperature service, even though the elastic region of the material behavior is exceeded. Since elastic methods should be adequately reliable, they necessarily are conservative to a certain degree compared with inelastic methods.

In the practical design, the elastic methods and rules currently in use, e.g. N 47 /1/ and RCC-MR /2/, are experienced to be rather conservative and thus often lead to either undesirable designs or inelastic analyses.

One of the crucial elements of the elastic design is the creep-fatigue evaluation on an elastic basis. So as to the SNR-2, less restrictive rules for the elastic creep-fatigue damage evaluation of Class 1 components are proposed. For this purpose two evident conservativisms shall be eliminated: (1) In the creep-damage evaluation: the relaxation of residual stresses during the hold-time period shall be taken into account rather than to assume the total initial stress being constant during the hold-time period (see Fig. 1); (2) In the fatigue-damage evaluation: to account for creep effects, the net relaxation strain during the hold-time period shall be added to the elastic-plastic strain range rather than to add the creep strains from constant stresses. Note: In the absence of reversed stresses during creep - which on the whole is the case in SNR-2 components - pure

creep strains merely contribute to the total accumulated strain but do not enlarge the cyclic stress-strain hysteresis loop (see Fig. 2).

2. Proposed Procedure

The creep-damage of the considered cycle followed by a hold-time period shall be calculated according to the following procedure (see Fig. 1):

$$U_C = U_{Crel} + U_{Csust}$$

$$U_{Crel} = \int_0^{t_h} \frac{dt}{t_r(\sigma(t)/0.9)}$$

= creep damage from a stress $\sigma(t)$ which relaxes uniaxially during the hold-time period t_h and whose initial value is the lesser of the maximum elastically calculated stress during the cycle and the 1.4-fold yield stress*)

$$U_{Csust} = \frac{t_h}{t_r(P/0.9)}$$

= creep damage from a stress P which is constant during the hold-time period t_h and whose value equals the equivalent primary membrane stress

$$t_r = \text{minimum time to creep rupture}$$

The fatigue-damage of the considered cycle followed by a hold-time period shall be calculated according to the following procedure:

$$U_F = \frac{1}{N_d}$$

$$N_d = \text{allowable number of stress cycles according to the design fatigue curve without hold-time for the total strain range } \epsilon_t$$

$$\epsilon_t = \epsilon_{elpl} + \Delta\sigma/E$$

$$\epsilon_{elpl} = \text{elastic-plastic strain range evaluated according to the established procedures}$$

$$\Delta\sigma = \text{uniaxial stress relaxation during the hold-time period with the initial stress value being the lesser of the maximum elastically calculated stress during the cycle and the 1.4-fold yield stress*)}$$

$$E = \text{Young's modulus}$$

*) If the elastic-plastic stress history during the cycle is known the stress at the end of the cycle (i.e. at the beginning of the hold-time period) may be taken as the initial value.

The creep-fatigue damage during the whole service life shall meet the condition

$$U_{CF} = \min \left[\frac{\sum_i n_i U_{Ci} + \frac{7}{3} \sum_i n_i U_{Fi}}{\sum_i n_i U_{Fi} + \frac{7}{3} \sum_i n_i U_{Ci}} \right] \leq 1$$

n_i = Number of individual cycles of loading condition i

Note that $\sum_i n_i t_{hi}$ must equal or exceed the total specified elevated temperature service life.

3. References

- [1] Class 1 Components in Elevated Temperature Service Section III, Division 1
ASME B&PVC Case N47, December 11, 1981
- [2] Règles de conception et de construction des matériels mécaniques des flots nucléaires RNR (RCC-MR), afcen, décembre 1983

Fig. 1: Stress relaxation

Fig. 2: Enlargement of stress-strain hysteresis loop by stress relaxation