



US005672667A

United States Patent [19]

DeSimone et al.

[11] Patent Number: **5,672,667**

[45] Date of Patent: ***Sep. 30, 1997**

[54] MULTI-PHASE POLYMERIZATION PROCESS

[75] Inventors: **Joseph M. DeSimone**, Chapel Hill; **Timothy Romack**, Durham, both of N.C.

[73] Assignee: **The University of North Carolina at Chapel Hill**, Chapel Hill, N.C.

[*] Notice: The term of this patent shall not extend beyond the expiration date of Pat. No. 5,530,077.

[21] Appl. No.: **637,896**

[22] Filed: **Apr. 25, 1996**

Related U.S. Application Data

[60] Continuation of Ser. No. 450,373, May 25, 1995, Pat. No. 5,530,077, which is a division of Ser. No. 409,880, Mar. 24, 1995, Pat. No. 5,527,865.

[51] Int. Cl.⁶ **C08F 2/16**

[52] U.S. Cl. **526/89; 526/255; 526/942**

[58] Field of Search **526/89, 255, 942**

[56] References Cited

U.S. PATENT DOCUMENTS

3,471,463	10/1969	Kagiya et al. .
3,522,228	7/1970	Fukui et al. .
4,499,249	2/1985	Nakagawa et al. .
4,748,220	5/1988	Hartmann et al. .
4,861,845	8/1989	Slocum et al. .
4,933,404	6/1990	Beckman et al. .
5,182,342	1/1993	Feiring et al. .
5,312,882	5/1994	DeSimone et al. .
5,328,972	7/1994	Dada et al. .
5,345,013	9/1994	Van Bramer et al. .
5,382,623	1/1995	DeSimone et al. .
5,530,077	6/1996	DeSimone et al. .

FOREIGN PATENT DOCUMENTS

0 301 532	2/1989	European Pat. Off. .
0 431 801 A2	6/1991	European Pat. Off. .
0 482 882 A1	4/1992	European Pat. Off. .
WO 93/20116	10/1993	WIPO .

OTHER PUBLICATIONS

T. Suwa et al; Melting and Crystallization Behavior of Poly(tetrafluoroethylene). New Method for Molecular Weight Measurement of Poly(tetrafluoroethylene) Using a

Differential Scanning Calorimeter; *Journal of Applied Polymer Science* 17, pp. 3253-3257 (1973).

J.M. DeSimone et al; Synthesis of Fluoropolymers in Supercritical Carbon Dioxide; *Science* pp. 1-3 (1992).

A.E. Feiring; Fluoroplastics; *Organofluorine Chemistry: Principles and Commercial Applications* pp. 339-372 (1994).

A.L. Logothetis; Fluoroelastomers; *Organofluorine Chemistry: Principles and Commercial Applications* pp. 373-396 (1994).

A.E. Feiring; Introduction to Fluorinated Polymers; *American Chemical Society Part 1*; pp. 1-59 (1992).

A.T. Worm; Introduction to Fluorocarbon Elastomers; *American Chemical Society Part 2*; pp. 1-40. (1992).

S.V. Gangal; Tetrafluoroethylene-Ethylene Copolymers; *Encyclopedia of Polymer Science and Engineering* 16, pp. 626-642 (1985).

M.B. King et al; The Mutual Solubilities of Water with Supercritical and Liquid Carbon Dioxide; *The Journal of Supercritical Fluids* 5, pp. 296-302 (1992).

Primary Examiner—Joseph L. Schofer

Assistant Examiner—N. Sarofim

Attorney, Agent, or Firm—Bell, Seltzer, Park & Gibson, P.A.

[57] ABSTRACT

The present invention provides a multi-phase polymerization process for making a water insoluble polymer. The process includes (1) providing a mixture comprising carbon dioxide and an aqueous phase, and containing a monomer and a polymerization initiator, and (2) polymerizing the monomer in the reaction mixture. The monomer may be a hydrocarbon or a fluorinated monomer. The polymerization initiator may be soluble in the aqueous phase, soluble in carbon dioxide, or insoluble in both the aqueous phase and carbon dioxide, such that the initiator forms a separate phase.

The present invention also provides multi-phase polymerization reaction mixtures useful in the process of making water insoluble polymers.

16 Claims, No Drawings